

Test Report 測試報告

Applicant: Jan Feng Co., Ltd.
申請廠商 展豐塑膠有限公司
No 2 Aly 3 Ln 11
Yajhou Rd Tucheng Dist. New Taipei City
Taiwan (R O C)
新北市土城區亞洲路 11 巷 3 弄 2 號

Number : TWNC01289586
報告號碼

Issue Date : Jul 31, 2024
報告發行日期

Sample Description 樣品敘述:

One (1) Group of Submitted Samples Said To Be:

壹(一)件所送檢樣品據指為:

Name of Sample : PE 發泡皮料

樣品名稱

Date Sample Received : Jul 23, 2024

樣品收到日期

Date Test Started : Jul 23, 2024

開始測試日期

Test Conducted 測試內容:


Tests were conducted by applicant's request, for details please refer to attached pages.

依據客戶要求執行測試，結果請參考附頁。

Authorized By 審核者:

On behalf of Intertek Testing Services
Taiwan Limited

全國公證檢驗股份有限公司



Matt Wang 王政雄
General Manager 總經理



Signed by 報告簽署人:



Thomas Chou 周世民
Manager 經理



Test Conducted 測試內容 :

Analysis of Food Utensils, Containers and Packages - Polyethylene (PE) as Raw Material
食品器具容器包裝檢測 - 原材料為聚乙烯(PE)

Method : Lead (Pb) / Cadmium (Cd)
檢驗方法 鉛含量 / 鎘含量

Sample was digested by microwave and analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).
樣品經微波消化後，以感應耦合電漿放射光譜儀(ICP-OES)測定。

Consumption of Potassium Permanganate
高錳酸鉀消耗量

Sample was migrated and migration solution was analyzed by titration.
樣品經溶出後，溶出液以滴定法測定。

Heavy Metals (as Pb)
重金屬(以 Pb 計)

Sample was migrated and migration solution was analyzed by colorimetry.
樣品經溶出後，溶出液以比色法測定。

Residues after Evaporation
蒸發殘渣

Sample was migrated and migration solution was weighted after evaporation.
樣品經溶出後，溶出液蒸發後秤重測定。

Migration of Phthalates
溶出塑化劑

Sample was migrated and migration solution was analyzed by Gas Chromatography-Mass Spectrometer (GC-MS).
樣品經溶出後，溶出液以氣相層析質譜儀(GC-MS)測定。

Phthalates
材質塑化劑

With reference to CNS 15138-1 (6/14/2012) - Method of test for determination of phthalates plasticizers in plastic products - Part 1: Gas chromatography/mass spectrometry.
參考 CNS 15138-1 (101 年 6 月 14 日) - 塑膠製品中鄰苯二甲酸酯類塑化劑試驗法-第 1 部：氣相層析質譜法。



Test Conducted 測試內容 :

Analysis of Food Utensils, Containers and Packages - Polyethylene (PE) as Raw Material

食品器具容器包裝檢測 - 原材料為聚乙烯(PE)

Result :
檢驗結果

Test Item 檢驗項目	Unit 單位	Limit of quantitation 定量極限	Result 檢出值 White plastic sheet (see arrow) 白色塑膠片 (見箭頭)	Limit # 限值
Material Test 材質試驗				
Lead (Pb) 鉛含量	ppm	5	Not detected 未檢出	100
Cadmium (Cd) 鎘含量	ppm	0.5	Not detected 未檢出	100
Di(2-ethylhexyl) Phthalate (DEHP) 鄰苯二甲酸二(2-乙基己基)酯(DEHP)	%	0.003	Not detected 未檢出	0.1
Di-n-octyl Phthalate (DNOP) 鄰苯二甲酸二正辛酯(DNOP)	%	0.003	Not detected 未檢出	0.1
Dibutyl Phthalate (DBP) 鄰苯二甲酸二丁酯(DBP)	%	0.003	Not detected 未檢出	0.1
Benzyl butyl Phthalate (BBP) 鄰苯二甲酸丁苯甲酯(BBP)	%	0.003	Not detected 未檢出	0.1
Di-isodecyl Phthalate (DIDP) 鄰苯二甲酸二異癸酯(DIDP)	%	0.003	Not detected 未檢出	0.1
Di-isononyl Phthalate (DINP) 鄰苯二甲酸二異壬酯(DINP)	%	0.003	Not detected 未檢出	0.1
Dimethyl Phthalate (DMP) 鄰苯二甲酸二甲酯(DMP)	%	0.003	Not detected 未檢出	0.1
Diethyl Phthalate (DEP) 鄰苯二甲酸二乙酯(DEP)	%	0.003	Not detected 未檢出	0.1



Test Conducted 測試內容 :

Analysis of Food Utensils, Containers and Packages - Polyethylene (PE) as Raw Material
食品器具容器包裝檢測 - 原材料為聚乙烯(PE)

Result :
檢驗結果

Test Item 檢驗項目	Unit 單位	Limit of quantitation 定量極限	Result 檢出值	Limit # 限值
			White plastic sheet (see arrow) 白色塑膠片 (見箭頭)	
Migration Test 溶出試驗				
Consumption of Potassium Permanganate 高錳酸鉀消耗量 (Water, 60°C, 30 min) (水、60°C、30分鐘)	ppm	0.2	0.5	10
Heavy Metals (as Pb) 重金屬(以 Pb 計) (4% Acetic Acid, 60°C, 30 min) (4% 醋酸、60°C、30分鐘)	ppm	1	< 1	1
Residues after Evaporation (pH>5) 蒸發殘渣(pH>5) (Water, 60°C, 30 min) (水、60°C、30分鐘)	ppm	1	1	30
Residues after Evaporation (pH≤5) 蒸發殘渣(pH≤5) (4% Acetic Acid, 60°C, 30 min) (4% 醋酸、60°C、30分鐘)	ppm	1	3	30
Residues after Evaporation (Food Containing Surface Oils / Oils and Fatty Foods) 蒸發殘渣(含表面油脂/脂肪性食品) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	1	7	150
Residues after Evaporation (Foods Containing Alcohol) 蒸發殘渣(含酒精成分食品) (20% Alcohol, 60°C, 30 min) (20%乙醇、60°C、30分鐘)	ppm	1	Not detected 未檢出	30



Test Conducted 測試內容 :

Analysis of Food Utensils, Containers and Packages - Polyethylene (PE) as Raw Material
食品器具容器包裝檢測 - 原材料為聚乙烯(PE)

Result :
檢驗結果

Test Item 檢驗項目	Unit 單位	Limit of quantitation 定量極限	Result 檢出值	Limit # 限值
			<u>White plastic sheet</u> (see arrow) 白色塑膠片 (見箭頭)	
Migration Test 溶出試驗				
Di(2-ethylhexyl) Phthalate (DEHP) 鄰苯二甲酸二(2-乙基己基)酯(DEHP) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.05	Not detected 未檢出	1.5
Dibutyl Phthalate (DBP) 鄰苯二甲酸二丁酯(DBP) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.05	Not detected 未檢出	0.3
Benzyl butyl Phthalate (BBP) 鄰苯二甲酸丁苯甲酯(BBP) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.05	Not detected 未檢出	30
Di-isononyl Phthalate (DINP) 鄰苯二甲酸二異壬酯(DINP) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.5	Not detected 未檢出	9
Di-isodecyl Phthalate (DIDP) 鄰苯二甲酸二異癸酯(DIDP) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.5	Not detected 未檢出	9
Di-2-ethylhexyl Adipate (DEHA) 己二酸二辛酯(DEHA) (n-Heptane, 25°C, 1 hour) (正庚烷、25°C、1小時)	ppm	0.05	Not detected 未檢出	18

: As per applicant's request with reference to MOHW Food No. 1111303439 Announcement (1/11/2023) - Sanitation Standard for Food Utensils, Containers and Packages.

依據客戶要求參考衛生福利部 112 年 1 月 11 日衛授食字第 1111303439 號公告「食品器具容器包裝衛生標準」

CNS : Chinese National Standards 中華民國國家標準

As requested by applicant, the test was conducted only on components listed in this report.

Other components were not tested.

依據客戶要求，僅測試列於此份報告的測試部位，其餘部位並未執行。



Sample photo 樣品照片 :

The tested part is indicated with the red arrow on the sample photo
樣品中紅色箭頭表示實際測試樣品部位



End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.

